

# Océ Specifications



## Océ Standard Paper, 90 g/m<sup>2</sup>

*Océ Standard Paper is a 90 g/m<sup>2</sup> paper with excellent printing capabilities for inkjet. This paper is the most commonly used paper for use as working drawings and high quality draft prints. Providing an economic alternative to premium grade paper, this standard paper has the extra durability needed for working drawings.*

Océ Imaging  
Supplies  
Product Info

IJM020  
*Wide-format CAD*  
Version 2

Physical properties	Weight	90 ± 3 g/m <sup>2</sup>	ISO 536
	Calliper	105 ± 3 microns	ISO 534
	Opacity	> 92 %	Elrepho 3000 D65 10XLAV
	Whiteness	160 ± 3 CIE	Elrepho 3000 D65 10XLAV

Available sizes & Available in all regular sizes.

For assortment details visit our [assortment](#), or supplies Web site at: <http://supplies.oce.com>

Article numbers

Storage conditions  
Temperature 10° - 30° C  
Relative Humidity 30-70 %  
Please repack opened rolls when not in use  
Allow material to adapt to room conditions 24 hours before printing

Shelf life  
Under normal storage conditions the shelf life of Océ inkjet Papers is 2 years. Higher humidity and/or temperature can effect the product performance.

Processing information  
Side to be printed is the outer side of the roll  
Best results between 15° - 25° C and 30-70 %RH (especially higher humidity will increase drying time, low humidity may cause curl)  
Daily check/cleaning of cartridges or printheads is recommended.  
Waste can be handled as paper waste

# Océ Standard Paper, 90 g/m<sup>2</sup>

---

Océ Imaging  
Supplies  
Product Info

---

IJM020  
*Wide-format CAD*  
Version 2

## Océ-Technologies B.V.

---



P.O. box 101  
5900 MA Venlo, the Netherlands  
+31 (0) 77 3592222  
[www.oce.com](http://www.oce.com)

Page 2 of 2

**Printing for  
Professionals**

© February 2003 Océ-Technologies B.V. Illustrations and specifications do not necessarily apply to the standard version of machines in all local markets. Technical specifications subject to change without prior notice. All products mentioned in this brochure are claimed as trademarks or registered trademarks of their respective companies.