Toner CrystalPoint™ WaterBased Ink UV Curable

Uncoated Papers

LFM091 Top Colour Paper FSC® 120 g/m²

Product Description

A high white, smooth, uncoated paper for high quality prints.

Physical Properties

Thickness	153 μm	ISO 534
Weight	120 g/m ²	ISO 536
Opacity	96.0 %	ISO 2471
Stiffness L&W MD/CD	280 / 160 mN	ISO 2493-1

Roughness (ml/min)	140	Bendtsen ISO 8791-2
Cobb 60 (g/m²)	25	ISO 535
Brightness UV D65 (%)	113.5	ISO 2470
CIE Whiteness	169	ISO 11475

All values listed are target values

Applications/ features

High quality posters and CAD drawings

FSC® certified EN 12281 and ISO 9706 certified ISO 14001 certified

Available Widths (mm)

3" core 594 841 914 1067

Refer for our current offering to www.canon-europe.com/mediaguide

Storage Conditions Temperature 21°C, Relative Humidity 50% Repack opened rolls when not in use.

Print Conditions

Best results are obtained between 20-27°C and 30-60% RH.

Environment, Health & Safety No Material Safety Data Sheet required. Paper waste suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot
yes	yes	yes

Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C

Outdoor Use This uncoated paper is developed for indoor use.

Colour

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on www.canon-europe.com/mediaguide

Environmental Certification





Processing Guidelines

Printing guidelines

It is recommended to handle the media with cotton gloves Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. Insert media with care in the printers. Incorrect loading can cause skewing or creasing. Allow material to adapt to room conditions for 24 hours before printing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printers.

Ink/toner restrictions and printer settings have to be set for specific printers to obtain the best results. Canon colour profiles include recommended ink restrictions and printer settings for Canon supported printers.

Application guidelines

When laminating CrystalPoint® prints pressure sensitive laminates are recommended. A laminator with soft rubber rollers is preferred. For optimal results temperature should be set between 55-60°C.

Standard disclaimer: All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

Canon Inc. canon.com Canon Europe canon-europe.com English edition 0615 © Canon Europa N.V., 2019

