

Product Description White, sturdy uncoated paper. The best paper for every day use. The paper provides good runnability, perfect toner adhesion, and high optical density on prints of all Océ Copy Press and Radiant Fusing printers.

Physical Properties

Weight	75 g/m ²		Roughness WS	259 ml/min	
Thickness	101 µm		Roughness TS	288 ml/min	
Opacity	92,8 %		Whiteness CIE	159	
Stiffness MD	142 mN		Brightness D65%	110	ISO2470
Stiffness CD	43 mN		L*; a*; b*	93,6; 3,5; -16,7	
Reflection R457+UV:	108		Porosity	675	
Reflection R457-UV:	88		Moisture content	4,1	
Tearing resistance: MD/CD	490/600				

Available

Widths (mm)

3" core: 297 mm 420mm 594mm 841mm 860mm 914mm | Refer to our current offering on <http://www.mediaguide.oce.com>

Storage Conditions

Temperature 10-20°C Relative Humidity 20 – 50%
 Repack opened rolls in plastic when not in use. Preferably, also those in the print engine overnight.

Print Conditions Best results are obtained between 10-30 °C and 40-70% RH.

Environment, Health & Safety No Material Safety Data Sheet required.

Printer Compatibility Refer to www.mediaguide.oce.com

Lamination Compatibility

Hot	Warm	Cold
1	1	3

3 = excellent 2 = fair 1 = not recommended

Hot, heat activated: 105 °C – 130 °C
 Warm, heat activated: 85 °C – 95 °C
 Cold, pressure sensitive

Outdoor Use Not suitable for outdoor use

Colour Profiles Océ develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on the download section of www.mediaguide.oce.com.

